



IGP-KORROPRIMER 1001

Priming powder for steel



IGP-KORROPRIMER 10 is mainly composed of epoxy resins, the corresponding hardeners, and the appropriate light-, heat-, chemical-, and corrosion-resistant pigments.

Technical Data Sheet

Characteristics

IGP Korropimers are corrosion resistant and have excellent chemical-resistance properties. All IGP powder varnishes, and water- and solvent-based top coats are suitable as finishing coats.

An adhesion test must be conducted for these liquid lacquer systems.

Application

Primer for blasted or zinc-phosphatised steel surfaces and galvanized substrates.

IGP-Korropimer 30 should be used for chromatised aluminium.

Product range

Surface aspects

- 1001A...A00, smooth finish, mat
Light grey, approx. RAL 7035 and traffic grey, approx. RAL 7043.
- 1001A...V00, smooth finish, mat, optimised degassing for galvanized substrates, iron grey, approx. RAL 7011 and telegrey 4, approx. RAL 7047

Powder specification

- Particle size: < 100 µm
- Solids: approx. 99 %
- Density: approx. 1.6 – 1.8 kg/l
- Storage stability: at least 12 months
- Storage temperature: < 25°C

Packaging

- Carton with inserted antistatic PE sack, contents 20 kg.
Carton with 25 antistatic PE sacks of 20 kg each; contents 500 kg.

Processing instructions

Pre-treatment

The substrate to be covered must be free of oxidation products, scale, oil, fat or release agent residue. For zinc and its alloys, a multi-stage chromatising process has proven to be best (DIN EN ISO 12487).

Material licence

The material licence is still being processed, in accordance with DIN EN ISO 12944 , part 6.



IGP Pulvertechnik AG
Industrie Stelz, Kirchberg
9500 Wil
Schweiz
Telefon +41 (0)71 929 81 11
Telefax +41 (0)71 929 81 81
www.igp.ch · info@igp.ch
www.doldgroup.com

IGP-KORROPRIMER 1001

Processing instructions

Outdoor use

A substrate made of steel must be blasted, preferably with electro corundum or conditioned cut wire shot. After blasting, the norm purity degree must be at least SA 2 ½ (white metal blast) in accordance with DIN EN ISO 12944-4. Further details can be found in this norm. Sharp edges, overlaps, etc., should be avoided (see DIN EN ISO 12944-3).

Indoor use

For heavy usage, steel metal sheet should preferably have a zinc phosphate treatment. For light use, (on iron or Zinkor), a complete de-greasing is adequate.

Coating equipment

IGP-Korroprimer 10 can be applied with all conventional electrostatic systems (corona- and tribo-charging). Regulations to be observed: VDE provisions and VDM information sheet 23471.

Information regarding application

The pre-defined stoving conditions must be observed. If stoving temperature is too high, the circulation air temperature should be limited to a maximum of 200 ° C, in order to avoid problems with intercoat adhesion. When curing thick steel components at increased temperatures, we recommend only allowing the primer to set followed by a complete stoving process together with the top coat.

When curing in directly heated gas stoves, a sample should be done in advance to ensure the intercoat adhesion with the following top coat. Please contact our technical customer support. In all cases, practical experiments adapted to the particular object and stoving oven are recommended, in order to determine the best possible stoving conditions. Our technical customer support would be happy to advise you. "Cup-shaped components" must be galvanized prior to coating if they are intended for outdoor use.

Curing conditions

Below, you will find temperature and time combinations that will result in adequate cross-linking of the coatings.

| Object temperature | retention time at object temperature |
|--------------------|--------------------------------------|
| 190°C | 10 -15 min. |
| 180°C | 20 - 25 min. |
| 170°C | 25 - 30 min. |

Technological values

To determine the following data, IGP-Korroprimer 10 was applied as follows:

- iron sheet metal, 0,8 mm, blasted
- coating thickness approx. 60 µm
- object temperature of 190°C, 10 min.

Ericksen cupping, DIN EN ISO 1520 > 3 mm
impact penetration, ASTM 2794 10 kg x cm
cross-cut adhesion test, DIN EN ISO 2409 GT 0

Chemical resistance properties

Coatings with «IGP-Korroprimer» show high resistance levels against many solvents and chemicals.

Preliminary test results for the powder coating system IGP-Korroprimer 10 as a priming powder and IGP-DURA® face 5807 as a top coating on blasted structural steel St 52 (surface preparation grade SA 2 ½) with a total layer thickness of approx. 140 - 160 µm, in accordance with DIN EN ISO 12944-6.

| Test | Evaluation before exposure | Condensate test in accordance with ISO 6270-2, 720 hours | Salt spray test in accordance with DIN EN ISO 9227, 720 hours | Salt spray test in accordance with DIN EN ISO 9227, 1440 hours | Condensate test in accordance with ISO 3231 with SO ₂ , 30 cycles |
|--|----------------------------|--|---|--|--|
| Cross-cut adhesion test, DIN EN ISO 2409 | 0 | 0 | 0 | 0 | 0 |
| Degree of blistering, DIN EN ISO 4628-2 | S (0) | S (0) | S (0) | S (0) | S (0) |
| Degree of rust, DIN EN ISO 4628-3 | | 0 | 0 | 0 | 0 |
| Fissure corrosion, mm DIN EN ISO 4628-8 | | 0 | 0 | 1 - 2 | 0 |
| Crack formation DIN EN ISO 4628-4 | | 0 | 0 | 0 | 0 |
| Degree of flaking, DIN EN ISO 4628-5 | | 0 | 0 | 0 | 0 |

Note

All verbal and written application-related advice that we administer and have determined through experiments is based on the best of our knowledge, but is to be seen as non-binding information and does not release you from your responsibility to conduct your own experiments. Application, use and processing of the products occur beyond our possibilities of control and therefore lie exclusively in your sphere of responsibility.



Powderful Solutions.